



ETFE Fluoropolymer Extruded Films

ETHYLENE TETRAFLUOROETHYLENE FILM FOR USE IN HIGH PERFORMANCE APPLICATIONS

TCI's ETFE films are produced from ethylene and tetrafluoroethylene co-polymer resin by melt extrusion casting process. ETFE films can be heat-sealed, thermoformed, and laminated to various substrates. These materials are ideally suited for architectural, solar, and mold release applications.

TCI's ETFE Film Characteristics

- Thickness range from 0.0005" to 0.010" (12 to 250 μ m)
- Standard width: 60" (1,524 mm)
- Width up to 62" (1,575 mm) available
- Any slit widths available upon request
- Bondable (plasma treated or chemically etched) surfaces available

- Broad continuous use temperature range from -328°F to 330°F (-200°C to 165 °C)
- Short term exposure of up to 400°F (204°C)
- Melt temperature minimum of 500°F (260°C)

- Excellent non-stick / release properties
- High elongation and tear resistance
- Excellent light transmission (>90%) and clarity, high transmittance of ultraviolet and all but far infrared wavelengths
- Superior weatherability in outdoor exposure

- High dielectric strength, 5,500 V/mil for 1-mil film (215 kV/mm for 25 μ m film)
- Free of plasticizers, processing aids, or additives
- Low permeability to liquids, gases, moisture, and organic vapors



TCI's ETFE Films Are Available In Two Grades:

ETFE PG (Premium Grade)

- Manufactured from 100% virgin premium grade ETFE resin
- ETFE PG is the grade of choice for applications requiring visual perfection
- ETFE's unique combination of high light transmission, clarity, and durability make it an invaluable material for applications such as architectural roofing, front glazing of solar panels, decorative, anti-graffiti, and greenhouses

ETFE MR (Mold Release Grade)

- ETFE MR is the material of choice for a release film in high temperature composite molding due to its superior non-stick properties and high upper use temperature in static applications
- Offers 20% higher area yield than FEP and PTFE: 110 ft²/lb. for 1 mil film (22.6 m²/kg for 25 μ m film)
- High elongation and excellent conformability to complex, contoured molds
- Standard colors include red and light blue, custom colors available upon request
- Available in a variety of perforated patterns

This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.

TEXTILES COATED INTERNATIONAL | Manufacturer of High Performance Fluoropolymer Films, Composites, and Laminates

200 Bouchard Street, Manchester, NH 03103 USA PHONE: (603) 296-2221 FAX: (603) 296-2248 www.textilecoated.com



ETFE Fluoropolymer Extruded Films

ETHYLENE TETRAFLUOROETHYLENE FILM FOR USE IN HIGH PERFORMANCE APPLICATIONS

			ETFE PG	ETFE MR
General Properties	Units	Test Method		
Specific Gravity		ASTM D792	1.74	
Area Yield	ft ² /lb/mil (m ² /kg/25μ)		110 (22.6)	
Flammability		UL-94	V-0	
Water Absorption	%		<0.03	
Mechanical Properties				
Tensile Strength	psi	ASTM D882	7,000 (48)	
Elongation at Break	%	ASTM D882	300	
Tensile Modulus	psi	ASTM D882	140,000 (965)	
Initial Tear Strength (2 mil film)	g	ASTM D1004	500	
Propagation Tear Strength (2 mil film)	g	ASTM D1922	75	
Folding Endurance (MIT)	cycles, ave.	ASTM D2176	>50,000	
Thermal Properties				
Continuous Use Temp	°F (°C)	UL-746 B	330 (165)	
Melt Point	°F (°C)	ASTM D3418	500 (260)	
Coeff. of Lin. Thermal Expansion	in/(in °F)	ASTM D696	4x10 ⁻⁵	
Electrical Properties				
Dielectric Strength (1mil film)	volts / mil	ASTM D149	5,500	n/a
Dielectric Constant 1kHz		ASTM D150	2.6	n/a
Dissipation Factor, 1kHz		ASTM D150	<0.0008	n/a
Optical Properties				
Refractive Index		ASTM D542	1.4	n/a
Solar Transmission	%	ASTM E424	90	n/a
Product Offering				
Width	inches (mm)		Up to 62" (1,575)	
Thickness	mils (μm)		0.5 - 10 (12.5 - 250)	0.5 - 2 (12.5 - 50)
Standard Colors			Clear	Blue, Red
Surface Treatments Available				
Chemical Etching			•	
Plasma Treatment				
Applications, Markets				
Composite Molding Process: Release Films				•
Chemical Process / Equipment			•	
Heat Sealing / Welding / Melt Adhesive			•	
Electrical / Electronics			•	
Medical			•	
Optical /Photovoltaics			•	
Protective/Decorative			•	

The above table contains typical representative values and is not to be used for product specification. Contact TCI for a formal specification.

This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.